

AEROSPEC® 400

Wide temperature range, multi-purpose, EP aerospace grease

Product Overview

ROCOL® AEROSPEC 400 is a high performance aerospace grease designed to give outstanding operational performance on a wide range of components including anti-friction bearings, plain bearings, gearboxes and other mechanisms over a wide temperature range.

ROCOL AEROSPEC 400 is a truly multi-purpose aerospace grease for an extensive range of applications including low temperatures, high temperatures and high loads.

Features and Benefits

- Temperature range from -54°C to +175°C ensures components are protected even on equipment working constantly in extreme sub-zero conditions.
- Lithium complex soap technology and EP additives provides outstanding high load performance.
- Fully synthetic base oil leaves minimal residues providing long life even at elevated temperatures.
- ROCOL AEROSPEC 400 is highly resistant to oxidation, providing extended lubrication intervals whilst reducing equipment failure, downtime and lubricant usage.
- Excellent corrosion resistance to protect in humid, damp and even wet conditions.
- ROCOL AEROSPEC 400 has extremely low start up and running torques even at temperatures down to -54°C.

Directions for Storage and Use

- ROCOL AEROSPEC 400 can be applied manually, by grease gun, keg pump or by other methods suitable for an NLGI No. 2 grease.
- Ensure all components are clean and free from any contaminants.
- It is recommended that the previous lubricant should be cleaned out prior to filling with ROCOL AEROSPEC 400.
- The storage temperature should be controlled between +1°C and +40°C.
- Shelf life is 3 years from date of manufacture.

Specifications

ROCOL AEROSPEC 400 is approved for use on:

- Boeing to MMS 657
- Airbus to 09-06-003

ROCOL AEROSPEC 400 meets the requirements of:

- SAE AMS 3058
- Airbus CML No. 03GCC1
- Joint Services Designation - XG-294
- Def Stan - 91-106/2
- NATO Code - G-1352
- NATO Stock Numbers:
 - 9150-99-855-1324 - 450g
 - 9150-99-376-9100 - 12.5kg

Pack Sizes

| Pack Size | Part Code |
|-----------|-----------|
| 380g | 16630 |
| 450g | 16637 |
| 3kg | 16638 |
| 18kg | 16634 |

AEROSPEC® 400

Wide temperature range, multi-purpose, EP aerospace grease

| Property | Test Method | Result |
|--|---------------------|----------------------|
| Appearance | Visual | Smooth beige grease |
| NLGI No. | IP 50 – ASTM D217 | 2 |
| Base Type | N/A | Synthetic fluid |
| Base Fluid Viscosity at 40°C | IP 71 | 50cSt |
| Base Fluid Viscosity at 100°C | IP 71 | 8cSt |
| Thickener | N/A | Lithium complex soap |
| Temperature Range | N/A | -54°C to +175°C |
| Drop Point | IP 132 | 280°C minimum |
| 4-Ball: | | |
| Weld Load | IP 239 – ASTM D2596 | 620kg |
| Mean Hertz Load | IP 239 – ASTM D2596 | 68kg |
| Low temperature torque (-54°C with 10% water) | | |
| Starting Torque | ASTM D1478 | 0.64Nm |
| Running Torque | ASTM D1478 | 0.23Nm |
| Copper Corrosion Test (24hrs at 100°C) | IP 112 – ASTM D130 | Pass |
| Water Washout (79°C) | IP 215 | 4.1% |

Values quoted above are typical and do not constitute a specification.

Safety Data Sheets

Safety data sheets are available for download from our website www.rocol.com or may be obtained from your usual ROCOL contact.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

Issue: 5 Date: 02-16