

Performance you can trust

AEROSPEC® 620

Perfluoropolyether grease suitable for a wide range of applications.

Aerospec 620 can lengthen relubrication periods dramatically due to its ability to resist degradation in hostile conditions. It is used in gearboxes, anti-friction and plain bearings, or any sliding surface such as pins, valves, plungers, screws etc.

Features

- Temperature range –46°C to 100°C
- Excellent chemical resistance
- Very long lubrication intervals in aggressive environments
- Excellent corrosion protection
- Excellent low temperature resistance

Directions for Use

- Apply manually or by suitable applicator capable of handling NLGI No 1 greases
- Compatible with most perfluoropolyether greases, however it is recommended that bearings be purged of previous lubricants before application
- If the previous lubricant used was not perfluoropolyether based, it is important to ensure that the bearings are fully cleaned with a suitable solvent, for example ROCOL Industrial Cleaner Rapid Dry Spray, before charging with Aerospec 620

T +44 (0) 113 232 2600
F +44 (0) 113 232 2740
E customer-service@rocol.com
www.rocol.com

ROCOL House, Swillington, Leeds LS26 8BS

Registered Company No. 559693 VAT No. 742 0531 67
Registered Office: Admiral House, St Leonard's Road, Windsor, Berkshire SL4 3BL

ROCOL A division of **ITW** Ltd



BS EN ISO 9001
Certificate No. FM 12448



BS EN ISO 14001
Certificate No. EMS 67596



OHSAS 18001
Certificate No. OHS 78173



INVESTOR IN PEOPLE

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

AEROSPEC® 620

Appearance	Soft white grease
NLGI No. (IP 50)(ASTM D217)	NLGI No. 1
Base type	Perfluoropolyether
Base fluid viscosity at 20°C	130 cSt
Thickener	PTFE
Temperature range	-46°C to 100°C
Shell 4 ball (IP 239)(ASTM D2596)	
Weld load	620 kg
Specific gravity	1.91
Solvent / Chemical Resistance	
All organic solvents	
All organic acids	Hydrochloric acid
Tributylamine	Hydrofluoric acid
Quinoline	Sulphuric acid
Potassium and sodium hydroxide	Orthophosphoric acid
Sodium carbonate	Ferric chloride / zinc chloride
Potassium chloride	Boron trifluoride
Aerospec 620 is soluble in:	Fluorinated solvents
Storage	Storage temperature should be controlled to between 1 and 40 °C.
Pack sizes – Part Codes	100g – p/c 16720

T +44 (0) 113 232 2600
 F +44 (0) 113 232 2740
 E customer-service@rocol.com
 www.rocol.com

ROCOL House, Swillington, Leeds LS26 8BS

Registered Company No. 559693 VAT No. 742 0531 67
 Registered Office: Admiral House, St Leonard's Road, Windsor, Berkshire SL4 3BL

ROCOL A division of *ITW* Ltd



BS EN ISO 9001
 Certificate No. FM 12448



BS EN ISO 14001
 Certificate No. EMS 67596



OHSAS 18001
 Certificate No. OHS 78173



INVESTOR IN PEOPLE

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.