

Technical Data

ROCOL[®]

Performance you can trust

SAFE STEP[®] Metal Primer

Part Code: 42087
Pack Size: 0.75 Litre



| | |
|-------------|--------|
| No of Pages | 03 |
| Issue No | 06 |
| Date | 6/20 |
| Ref | SSMPTD |

Description

SAFE STEP[®] Metal Primer is a solvent based, 2 pack epoxy resin pigmented with zinc phosphate. It is designed for use as a high-performance primer for blast cleaned steel, aluminium and galvanising. It gives excellent corrosion protection in even the most extreme environments.

SAFE STEP[®] Metal Primer should be applied onto a suitably prepared surface prior to the application of the SAFE STEP[®] range of floor finishes to promote effective adhesion and corrosion protection between the substrate surface and the floor finish.

Technical Data (Typical)

| | |
|--|--|
| Colour: | Grey |
| Pack Size: | 0.75 litre |
| Useable Life When Mixed @ 20°C: | 4 hours |
| Curing Times: Touch Dry: Hard Dry: Full Cure Time: | 2 hours @ 21°C 16 hours @ 21°C 7 days @ 21°C |
| Over-coating Time: | Minimum of 6 hours @ 20°C Maximum 3 months |
| Application Film Thickness | 88-100µm wet film thickness 75-85µm nominal dry film thickness |
| Theoretical Coverage Per litre: This figure makes no allowance for substrate profile, porosity, uneven application or losses in containers or rollers/brushes. Soft Roller/Brush: | 10m ² @ 100 microns wet film thickness |
| Shelf Life: | 2 years |
| Flash Point: | 36°C |
| Application Temperature: | Do not apply when relative humidity exceeds 90% Do not apply when ambient temperature is below 10°C |
| Storage Conditions: | 5-30°C |
| EU limited value for this product (Cat A/j):550g/l (2007) / 500g/l (2010) | This product contains max. 165g/l VOC |
| Volume Solids (BS3900 part A10): | 85% |
| Density (Mixed) - BS3900A19 | 1.5 g/cm ³ (mixed) |

T +44 (0) 113 232 2600
F +44 (0) 113 232 2740
E customer-service@rocol.com
www.rocol.com

ROCOL House, Swillington, Leeds LS26 8BS

Registered Company No. 559693 VAT No. 742 0531 67
Registered Office: Admiral House, St Leonard's Road, Windsor, Berkshire SL4 3BL

ROCOL A division of **ITW** Ltd



BS EN ISO 9001
Certificate No. FM 12448



BS EN ISO 14001
Certificate No. EMS 67596



OHSAS 18001
Certificate No. OHS 78173



INVESTOR IN PEOPLE

Technical Data

ROCOL®

Performance you can trust

| | |
|-------------------------|---|
| Mixing Ratio by Volume: | 5 parts base component 1 part hardener component |
| Flammability: | Highly flammable |
| Cleaning Solvent: | Xylene |

Surface Preparation

Steel: should be blast cleaned in accordance with SA 2.5 minimum. SA 3 is recommended for conditions of severe exposure. Oil and grease should be completely removed using solvent (Xylene). Surface profile should be no more than 60 microns for one coat of primer. If the profile is more than 60 microns, more than one coat may be required.

Where blast cleaning is carried out after erection of assembly, special attention should be paid to corners, edges, nuts, bolts, welds, etc. Welds should, if necessary, be ground and all weld spatter, slag, etc. should be removed.

Aluminium: should be phosphate treated. Where this is not available, the surface should be abraded with 180 grade abrasive paper.

Galvanised Steel: new galvanising needs only to be degreased prior to application. Old galvanising must be abraded to remove corrosion deposits.

GRP: abrade with course 240 grade abrasive paper.

For more detailed surface preparation on metal or other surfaces contact ROCOL® Site Safety Systems Technical Department.

Application Instructions

Do not part mix units.
Incorrectly mixed product will affect performance or cause premature failure of the coating.

Mixing of Components

Stir the contents of the base container (Part A) carefully ensuring that all the solids are removed from the bottom using a suitably sized implement. Carefully add all the contents of the hardener container (Part B) and stir thoroughly into the base. Continue stirring until both components are properly mixed and a uniform colour is obtained. (Mix for at least 5 minutes.)

Mixing

1. Pour all the contents of the hardener component into the base component. Larger packs should be accurately proportioned if required.
2. Mix thoroughly with a mechanical mixer for 2 minutes. Ensure all material is scraped from sides of the container and continue mixing for a further 2 minutes. Avoid air entrapment.
3. Product should be used immediately after mixing.
4. Failure to mix components correctly will result in incorrect curing and/or failure of the coating

Application Methods

Can be applied by airless spray, conventional air spray, brush or soft roller.

Airless spray typical spray settings

Devilbiss airless 32:1 pump ratio
Tip size 13-15 thou
Input air pressure 60 psi

Note: When airless spray is being used, excessively high tip pressure should be minimised.

T +44 (0) 113 232 2600
F +44 (0) 113 232 2740
E customer-service@rocol.com
www.rocol.com

ROCOL House, Swillington, Leeds LS26 8BS

Registered Company No. 559693 VAT No. 742 0531 67
Registered Office: Admiral House, St Leonard's Road, Windsor, Berkshire SL4 3BL

ROCOL A division of **ITW** Ltd



BS EN ISO 9001
Certificate No. FM 12448



BS EN ISO 14001
Certificate No. EMS 67596



OHSAS 18001
Certificate No. OHS 78173



INVESTOR IN PEOPLE

Technical Data

ROCOL[®]

Performance you can trust

Brush/Roller

Good quality brushes and mohair rollers should be used.

Welding/Cutting

Areas to be cut or welded should be masked off before application of the SAFE STEP[®] Metal Primer. Ensure that all edges, corners, bolt holes etc. are adequately covered.

When to Prime

Exterior surfaces should be primed immediately after blast cleaning. Surfaces cleaned within shops should be primed within 4 hours (see details of over-coating times).

Limitations

Primer not to be applied when the relative humidity exceeds 90% or the ambient temperature is below 7°C.

Health & Safety

Refer to Safety Data Sheet before use.

Safety Data Sheets – Safety data sheets are available for download from our website www.rocol.com or may be obtained from your usual ROCOL[®] contact.

Disclaimer: *The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which may affect the use and performance of our products, for this reason it is given without responsibility.*

T +44 (0) 113 232 2600
F +44 (0) 113 232 2740
E customer-service@rocol.com
www.rocol.com

ROCOL House, Swillington, Leeds LS26 8BS

Registered Company No. 559693 VAT No. 742 0531 67
Registered Office: Admiral House, St Leonard's Road, Windsor, Berkshire SL4 3BL

ROCOL A division of **ITW** Ltd



BS EN ISO 9001
Certificate No. FM 12448



BS EN ISO 14001
Certificate No. EMS 67596



OHSAS 18001
Certificate No. OHS 78173



INVESTOR IN PEOPLE